



Giltgrip 22 Carpet Adhesive

PRODUCT DESCRIPTION

Giltgrip 22 is a water-based Latex adhesive with low in VOC and has been specifically formulated to provide extra open time for positioning of long runs of commercial carpet before it develops its "leggy" grab and holding power for jute & action backed tufted carpets, woven wilton & axminster carpets and most needle-punched carpets.

FOR BONDING

Tufted secondary backed carpets (jute, soft and action-backed), woven wilton & axminster carpets, most needle-punched carpets as well as cushioned Double Bond underlays.

TO

Sound, smooth dry subfloors of concrete; conventional sand/cement screeds or underlayment; plywood; hardboard or cement sheet underlays.

STANDARDS

Australian/NZ Standard 2455.1.2007 – "Textile Floor Coverings Installation Practice".

SURFACE PREPARATION

All surfaces to be bonded shall be dry, smooth, sound and clean. Subfloors must also be free of wax, grease and hydrostatic pressure. The minimum subfloor temperature before commencing surface preparation and adhesive application is 10⁰C. It is recommended that all absorbent substrates be primed with a suitable Acrylic Primer prior to the application of adhesive.

APPLICATION

Apply using a 'V' notched trowel spreader, 1.6mm x 1.6mm x 1.6mm giving a spread rate up to 5m²/litre to adhere the double bond underlay to the entire subfloor area. Use a 2.4mm x 2.4mm x 2.4mm 'V' notched trowel giving a spread rate up to 3m²/litre to adhere smooth back carpet to subfloors or double bond underlay or 3.2mm x 1.6mm x 3.2mm 'V' notched trowel giving a spread rate up to 2m²/litre for coarse back, woven or action back carpets to subfloors or double bond underlay.

Check to ensure that complete transfer of adhesive to the carpet/underlay has occurred. Roll finished installation with a 25-35Kg roller. Complete the installation according to the adhesive manufacturer's instruction. Do not allow heavy traffic for 24 hours. All Seams should be seamed sealed using a suitable seam sealer. It is strongly recommended that Dual bond seaming tape be used on all seams in double bond installations.

CLEAN UP

Clean tools immediately after use with warm soapy water. Dried adhesive may be cleaned off using a solvent cleaner applied to a damp cloth then rubbed gently over the dried adhesive.

SHELF LIFE

Up to 12 months in sealed container at 20⁰C.

SAFETY & HANDLING

A Material Safety Data Sheet is available on request.

STORAGE

Recommended to be at temperatures between 15 and 25 degrees Celsius. Keep in well-ventilated area away from sources of heat.

TECHNICAL DATA

Appearance: Cream / White
Solids: Approx 60%
Base Polymer: Latex
Viscosity: 50,000 to 60,000 cps
Toxicity: Non-toxic
S.G.: 1.25

CONTAINER SIZES

15 litre plastic pails

Every Flooring Installation Deserves the "GILT EDGE" Finish

Auckland
37 Fairfax Ave
Penrose
Ph 09 579 7067
Fax 09 579 7064

Auckland
3/7 Colway Place
Glenfield
Ph 09 443 7067
Fax 09 444 0510

Whangarei
2 Mill Road
Ph (0274) 364 642

Hamilton
40 Te Kowhai Dr
Te Rapa
Ph 027 223 4147

Tauranga
45 Totara St
Mt Maunganui
Ph 027 223 4147

Palmerston North
1021 Tremaine Ave
Ph 0274 364 646

Wellington
50 Fitzherbert St
Petone
Ph 04 569 7067
Fax 04 569 7066

Christchurch
47 Carlyle St
Sydenham
Ph 03 379 7067
Fax 0800 103 649

Timaru
17 Butler St
Ph (0274) 387 266

Dunedin
15 Turakina Rd
South Dunedin
Ph 03 455 7067
Fax 03 455 7069

Nelson
8 Washington Rd
0274 387 266