



Roberts 41 Primer is a co-polymer acrylic emulsion designed to prime absorbent internal concrete substrates prior to the application of Roberts cementitious compounds. It improves adhesion and eliminates or minimises bubbling in the finished compound.

For Non-Porous substrates use Roberts 34 Super Primer.

Preparation

Sub floor must be free of oil, grease, wax, curing compounds, dust, old adhesive and any other contaminations, which may inhibit bond.

Diamond grinding, shot blasting or scarifying is the preferred method of preparation for large areas to remove any contamination.

Note:

Concrete floors must be dry in accordance with A.S. 1884 - 1985 Appendix A 70% Relative humidity maximum.

Mixing

Shake container well before mixing with clean water. Roberts 41 primer is diluted with clean water in equal parts (1:1)

Application

Apply an even thin film with a soft broom or roller and allow to dry to a clear thin film for approximately 3 hours. Do not leave longer than 24 hours before applying underlayment.

Very absorbent concrete may require a second coat of 41 Primer.

Clean Up

Clean all equipment with water immediately after use

Packaging

5 ltr and 20 litre containers.

Storage

Store in cool dry area out of direct sun light and protect from frost

Coverage

Approximately 8 to 12 sq.m per litre (1:1) depending on texture of substrate.

Shelf Life

12 months in unopened container.

Safety & Handling

Material Safety Data Sheet available upon request.