

BETTALAY

Specialised Flooring Underlay System

Usage

For double-stick installation in commercial areas where a greater level of staff and client comfort is needed.

| Property | Requirement | BETTALAY (Typical) | Test |
|--|--|-----------------------|------------|
| Thickness (mm) | | 6.5 + -0.3 | BS 4051 |
| Weight (g/m ²) | | 1430+ -40 | AS 2111-3 |
| Backing | | | |
| Topside | | Textron | |
| Downside | | Woven polypropylene | |
| Elongation % @ applied forces of 40N | | 2% | BS 2567 |
| Work of Compression (J/m ²) | Min 50 Max 200 | 80 | BS 4098 |
| Retention of W.O.C. after dynamic loading | Min 40% original | 90% | BS 4098 |
| Deflection @ 100kPa after 1,000 cycles | Min 2mm Max 7mm | 4.0mm | BS 4098 |
| Loss of Thickness | | | |
| Static loading after 24 hrs | 15% Max | 10% | BS 4939 |
| Dynamic loading after 24 hrs | 15% Max | 7% | BS 4052 |
| Fire Propagation (AS2404) | Pass | Passes | AS 2111-18 |
| Impact noise reduction @ 1,000 Hz(dB) | | 49 | ISO 150/8 |
| Adhesive | Roberts 80, GS100, Direct & Double SF, Polymer 227, Polymer 220 Polymer 300 | | |

Advantages

Double-stick system means rapid installation with no rucking or stretching of carpet. Up to 50% increase in carpet life compared with conventional & direct-stick methods.

Anti-microbial. Anti-allergenic.

Packaging

Green bag 10 lin.m x 1.83m 26.5+-1.0kg/roll. Available ex-stock

Distributed by: Gilt Edge Industries Ltd

Chch ph 03 379 7067; Dndn ph 03 455 7067; Well ph 04 569 7067; Akld ph 09 443 7067

Free Fax 0800 103 649