



Gilt Edge Industries Ltd[®]

TECHNICAL DATA SHEET

Customer Services
CHC : 03 379 7067 or AKL: 09 443 7067
Email: help@giltedge.co.nz

Technical & Sales Assistance
Email: help@giltedge.co.nz
www.giltedge.co.nz

TECHNICAL DATA

Gilt Grip BONDUX™ SUPER C POLYURETHANE ADHESIVE

DESCRIPTION

A single pack high strength low-foaming moisture curing polyurethane based adhesive.

USES

Bonding most types of resilient and rubber flooring/underlay/acoustic products to concrete and timber substrates. Due the highly variable nature of rubber and resilient products in the market contractors should test lay a typical sample and do a destructive pull test to confirm adequate adhesion to a given substrate.

COLOUR

Beige and Grey

FEATURES

Highly thixotropic for no-slump application
Extremely high bond strength
Rapid cure- usually allowing careful traffic/unclamping in 4 hours
Good wet grab and firm initial hold
Suitable for intermittent immersion service in water once cured
Low smell
Low foaming (high density foam) to gap fill
VOC free
New technology (NZ Patent Application No 554101)

SURFACE PREPARATION

Surfaces should be clean and sound. Contact GEI for specific recommendations. Contractors should test lay a typical sample and do a destructive pull test to confirm adequate adhesion to a given substrate.

Moisture content of substrate should not exceed levels stated in the AS/NZ flooring AS/NZ 1884 -1985

Use VBS 3.6lt pack or Protectcrete Moisture Fix/ Densiproof if substrate exceeds these standards. Contact GEI for instruction.

MIXING RATIO

Single pack. Cures by reaction with moisture from the atmosphere and the substrate.

APPLICATION

Remove foil bag from container, and massage to fluidise contents. Cut corner off bag sufficient to express adhesive as required.
Fold and clamp foil to seal after use.
Trowel onto substrates with a suitable notched trowel. The product is highly thixotropic in the container, but quickly breaks down to an easy trowelling no-slump consistency with when applying. A good starting point for trowel configuration is a minimum 1.6mm V Notch depending on the substrate and type of flooring product being installed

Lay directly onto prepared glue with minimum of sideways movement.
Bed in firmly to ensure effective contact with all surfaces to be bonded.
Fastening is recommended to secure during cure.
Remove excess promptly. Do not return mixed product to resin container.

Consult GEI for specific recommendations.

TECHNICAL DATA

Packaging:	12kg plastic pails with foil bags / 600g sausage.
Coverage Rate:	3 - 5 m ² per kg dependent on substrate and specific rubber product being installed..
Cure Time:	See notes below * Normally initial set in 4 hours (trafficable with caution), safe to traffic after 12 hours. Full cure 7 days.
	*Note Product needs moisture in at least one substrate to effect cure. Cure will be slower in wide joints, at low temperatures (< 5° C) in low humidity and when used on moisture impervious surfaces. Consult GEI for specific advice under these conditions.
Working Time:	Approximately 30 minutes once applied, depending on ambient conditions.
Shelf Life:	Six months in unopened containers. Opened pails may skin and this may be cut off and remaining product used.
Clean Up:	Clean up frequently using Uroxsys Polyurethane Brush Cleaner before product has set on equipment.
SAFETY DATA:	Wear protective clothing. Gloves are essential. Avoid contact with skin. For further information refer to material safety data sheet.

This information is, to the best of our knowledge, true and accurate, but any recommendations or suggestions which may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

BondSuperC TD1/05/07 DP60.11